

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C09C 1/00	A1	(11) International Publication Number: WO 97/46624 (43) International Publication Date: 11 December 1997 (11.12.97)
(21) International Application Number: PCT/US97/09380 (22) International Filing Date: 3 June 1997 (03.06.97) (30) Priority Data: 08/657,311 3 June 1996 (03.06.96) US 08/867,589 2 June 1997 (02.06.97) US (71) Applicant: ENGELHARD CORPORATION [US/US]; 101 Wood Avenue, P.O. Box 770-0770, Iselin, NJ 08830 (US). (72) Inventors: SULLIVAN, William, J.; 217 North Highland Avenue, Ossining, NY 15062 (US). ELLIOT, Patricia; 45 Circle Drive, Irvington, NY 10533 (US). FLEMING, Dana; 1 Partridge Hill Road, Hyde Park, NY 12538 (US). (74) Agents: MEILMAN, Edward, A. et al.; Ostrolenk, Faber, Gerb & Soffen, LLP, 1180 Avenue of the Americas, New York, NY 10036 (US).		(81) Designated States: AL, AM, AT, AU, AZ, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, UZ, VN, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: PEARLESCENT GLASS (57) Abstract A pearlescent pigment comprises C glass flakes having a layer comprising rutile titanium dioxide or iron oxide thereon. A hydrous layer of the rutile forming titanium dioxide or iron oxide is formed on the glass flakes and the resulting coated flakes are calcined. Titanium dioxide or iron oxide coated glass flakes are further coated with absorption pigments.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

- 1 -

PEARLESCENT GLASSBACKGROUND OF THE INVENTION

This is a continuation-in-part of application Serial No. 08/657,311, filed on June 3, 1996.

5 Imparting a pearlescent luster, metallic luster and/or multi-color effects approaching iridescent can be achieved using a nacreous or pearlescent pigment which comprises a metal oxide-coated platelet. These pigments were first described in U.S. Patents 3,087,828 and
10 3,087,829 and a description of their properties can be found in the Pigment Handbook, Vol. I, Second Edition, pp. 829-858, John Wiley & Sons, N.Y. 1988.

 The oxide coating is in the form of a thin film deposited on the surfaces of the platelet. The oxide in
15 most wide spread use at present is titanium dioxide. The next most prevalent is iron oxide while other usable oxides include tin, chromium and zirconium oxides as well as mixtures or combinations of oxides.

 The coating of the metal oxide on the platelet
20 must be smooth and uniform in order to achieve the optimum pearlescent appearance. If an irregular surface is formed, light scattering occurs, and the coated platelet will no longer function as a pearlescent pigment. The metal oxide coating must also adhere
25 strongly to the platelet or else the coating will be separated during processing, resulting in considerable breakage and loss of luster.

 During the preparation of these coatings on the platelets, particles which are not attached to the

- 2 -

platelet may form. These small particles cause light scattering and impart opacity to the pigment. If too many small particles are present, the pearlescent appearance may be reduced or lost. The addition of these metal oxide coatings to a platelet so that the luster, color and color homogeneity are maintained is a very complex process, and to date, the only platy substrate which has achieved any significant use in commerce is mica.

A wide variety of other platy materials have been proposed for use as a substrate for forming these pearlescent pigments. These include non-soluble inorganic materials such as glass, enamel, china clay, porcelain, natural stones or other siliceous substances, metal objects and surfaces of organic polymer materials such as polycarbonate. See, e.g., U.S. Patents 3,123,485, 3,219,734, 3,616,100, 3,444,987, 4,552,593 and 4,735,869. While glass has been mentioned as a possibility on many occasions, for instance in U.S. Patent 3,331,699, commercial pearlescent products are not made using glass and experience has shown that products made using glass as the platelet substrate have rather poor quality.

Said U.S. Patent 3,331,699 discloses that glass flakes may be coated with a translucent layer of particles of a metal oxide having a high index of refraction, such as titanium dioxide, provided there is first deposited on the glass flakes a nucleating substance which is insoluble in the acidic solution from which the translucent layer of metal oxide is deposited. The patent does not mention the necessity of a smooth transparant film, not particles, being necessary for quality interference pigments to be developed. The

- 3 -

patent teaches that the nature of the glass is not critical, but that the presence of the nucleated surface is critical. It is further stated that there are only a small number of metal oxide compounds which are insoluble in the acidic solution and capable of forming a nucleated surface on the glass flakes; tin oxide and a fibrous boehmite form of alumina monohydrate are the only two such materials disclosed. As demonstrated in the examples below, products prepared according to the teachings of this patent are poor in quality.

U.S. Patent 5,436,077 teaches a glass flake substrate which has a metal covering layer on which is formed a dense protective covering layer of a metal oxide such as a titanium dioxide. In this patent, the nature of the glass is unimportant, the metallic coating provides the desired appearance and the overcoating of the metal oxide is present to protect the metallic layer from corrosive environments.

It has now been determined that there is a method for preparing smooth, uniform coatings of metal oxides on glass flakes which adhere to the glass flakes to yield high quality pearlescent pigments and it is accordingly the object of the present invention to provide such a method and to provide such metal oxide coated glass flake pearlescent pigments which result from that method. It is also possible to make combination pigments containing absorption pigments which are not soluble in water and which cannot be formed in place from a water-soluble reactant or reactants.

30 SUMMARY OF THE INVENTION

The present invention relates to a pearlescent pigment and to a method for the production of such a

- 4 -

pigment. The resulting pigment can be used in any application for which pearlescent pigments have been heretofore used such as, for example, in cosmetics, plastics, inks and coatings including solvent or waterborne automotive paint systems.

DESCRIPTION OF THE INVENTION

In accordance with the present invention, a pearlescent pigment is formed by establishing a hydrous film layer of titanium and/or iron oxides on glass flakes and thereafter calcining the coated flakes provided that the glass flakes employed are C glass flakes and when the hydrous layer is titanium, the procedure is a rutilizing procedure.

Glass flakes are desirable in the industry because they are very resilient and can be optically attractive as well. The glass is primarily composed of SiO_2 and Al_2O_3 and can also include ZnO , CaO , B_2O_3 , Na_2O and K_2O as well as FeO and Fe_2O_3 . The glass flakes are made by stretching a molten glass into thin sheets, beads or glass tubes followed by crushing the glass into flakes. Large hollow spheres can be produced followed by solidification and crushing as well as a variety of other flake production methods. The flakes have a size and shape mimicking the mica platelets used in the TiO_2 and Fe_2O_3 -coated mica pearlescent pigments and thus have an average particle size in the range of about 1 to 250 microns and a thickness of about 0.1-10 microns. More cubic flakes having similar particle sizes and thickness of about 10-100 microns can be utilized, however, the pearlescent effect is significantly diminished due to the low aspect ratio.

- 5 -

Glass can be classified as A glass, C glass or E glass. The A glass is a soda-lime glass and is commonly used to make windows. It contains more sodium than potassium and also contains calcium oxide. C glass, also known as chemical glass, is a form of glass which is resistant to corrosion by acid and moisture. It often contains zinc oxide as well as other oxides which makes the flakes more resistant to chemical destruction. E glass or electrical glass is, as the name implies, designed for electronic applications and although it is very stable at high temperatures, it can be susceptible to chemical attack. The following table shows the composition of several commercial samples of A, C and E glasses in weight percent. It is recognized that C glass as well as A and E glass have broad windows regarding their chemical composition and in fact A and E glass compositions can be made very similar to C glass.

TABLE 1

Type	A Glass	C Glass	C Glass	E Glass	E Glass
SiO ₂	72.5	65-70	65%	52-56	52.5
Al ₂ O ₃	0.4	2-6	4%	12-16	14.5
CaO	9.8	4-9	14%	20-25	22.5
MgO	3.3	0-5	3%	0-5	1.2
B ₂ O ₃	0.0	2-7	5.5%	5-10	8.6
Na ₂ O+K ₂ O	5.8	9-13	8.5%	<0.8	<0.5
ZnO	-	1-6	0	-	-
FeO/Fe ₂ O ₃	0.2	-	0	-	0.2

In the practice of the present invention, the C or chemical type glass is preferred. While metal oxide

- 6 -

coatings on A or E glass can be prepared, the resulting pigments do not have the quality of the products as C glass and hence have limited commercial value. When TiO_2 coated products are prepared, anatase or rutile crystal modifications are possible. The highest quality and most stable pearlescent pigments are obtained when the TiO_2 is in the rutile form. Also the glass used can influence the crystal form of the titanium dioxide coating. For instance, when common E glass is used, the resulting crystal phase is primarily anatase. In order to obtain rutile, an additive must be used which can direct the TiO_2 to the rutile modification.

The coating of the glass flakes with titanium dioxide or iron oxide generally follows procedures known in the art for the formation of TiO_2 -coated or iron oxide-coated mica. Mica is anatase directing and, as noted earlier, most glass also appears to direct titanium dioxide coatings to the anatase crystalline form. At least some rutile formation is necessary to obtain higher quality and more stable products.

In general, the procedure involves the dispersing of the glass flake particulate and combining that dispersion with a precursor which forms a hydrous titanium oxide or iron oxide film coating on the flakes.

In the coating process, the glass flakes are dispersed in water, which is preferably distilled. The average particle size which is preferably used can vary from an average of about 3 microns to an average of about 150 microns and a flake thickness of 0.1-25 microns although larger flakes can also be used if so desired. The concentration of the glass flake in water can vary from about 5% to 30% although the generally preferred concentration varies between about 10% to 20%.

- 7 -

After the glass is dispersed in the water and placed in an appropriate vessel, the appropriate titanium or iron source materials are introduced. The pH of the resulting dispersion is maintained at an appropriate level during the addition of the titanium or iron by use of a suitable base such as sodium hydroxide to cause precipitation of the hydrous titanium dioxide or hydrous iron oxide on the glass flakes. An aqueous acid such as hydrochloric acid can be used for adjusting the pH. The coated platelets can, if desired, be washed and dried before being calcined to the final pearlescent pigment.

The source of the iron is preferably ferric chloride although any other iron source known in the prior art can be employed. The source of the titanium is preferably titanium tetrachloride although, similarly, other sources known in the art can be employed. If desired, layers of titanium and iron can be deposited sequentially.

In the case of titanium dioxide, the modifications of the foregoing procedure to realize a rutilization procedure are known in the prior art. In one procedure, a layer of hydrous tin oxide is first precipitated on the surface of the glass flakes followed by the layer of hydrous titanium dioxide. When this layered combination is processed and calcined, the titanium dioxide is oriented in the rutile form. The procedure is described in detail in U.S. Patents 4,038,099, which is incorporated herein by reference. An alternate procedure involves the deposition of the hydrous titanium dioxide on the glass flakes in the presence of iron and calcium, magnesium and/or zinc ions without the use of tin. This is described in detail in

- 8 -

U.S. Patent 5,433,779, the disclosure of which is hereby incorporated by reference.

Combination pigments can be made as described in U.S. 4,755,229, the disclosure of which is
5 incorporated herein by reference. Briefly, an aqueous dispersion of the colored pigment containing an anionic polymeric substance is added to a suspension of the pigment. The hydrous oxide of a polyvalent metal is then produced by the simultaneous addition of a solution of
10 the metal salt and of a basic solution. The dispersed pigment particles and the polymer deposit with the hydrous oxide of the polyvalent metal to form a smooth, adherent, uniform coating on the pearlescent glass.

In order to utilize an insoluble absorption
15 pigment successfully in combination pigments, the insoluble pigment must be very highly dispersed. A convenient starting point is the dry pigment or preferably an aqueous presscake of the pigment. After dilution with water or other liquid, such as alcohol,
20 dispersion is achieved by any one of the usual techniques, such as milling, high shear mixing, or application of ultrasonic energy. The desired degree of dispersion is similar to that conventionally used in paint and coating formulations. It is preferred to add
25 the anionic polymer prior to or during the dispersion step in order to assist the dispersion process.

The polymer-absorption pigment dispersion is combined with a suspension of coated glass pigment. The pH of the resulting suspension should be in the range
30 suitable for precipitation of the desired polyvalent cation hydroxide or hydrous oxide, generally between about pH 1 and 11, and most frequently between about pH 2 and 8. A solution of soluble salt of the polyvalent

- 9 -

cation is then added to the suspension simultaneously with a quantity of a basic material soluble in the solution sufficient to maintain the pH in the desired precipitation range. The absorption pigment is deposited
5 on the platelets to form a smooth, uniform, colored coating. The suspension can then be filtered, and the filter cake washed with water and dried, for example, at 120°C, to produce an easily dispersible powder of the combination pigment.

10 Absorption pigments which are water insoluble, transparent (i.e. substantially non-light scattering) and which cannot be formed in situ from a water soluble reactant(s) but which may be highly dispersed in water or water-alcohol containing anionic polymer are suitable for
15 the invention. These include, for example, carbon black and organic pigments in the following groups: azo compounds, anthraquinones, perinones, perylenes, quinacridones, thioindigos, dioxazines, and phthalocyanines and their metal complexes. The pigments,
20 depending on their color intensity, are used in a concentration range of about 0.01% to about 30% based on the weight of pigment, preferably 0.1% to 10%.

The useful polymers are those which are capable of precipitating with polyvalent cations at the
25 appropriate pH values. Thus, the polymers are usually anionic, or, like proteins, have both anionic and cationic groups. Useful polymers include albumin, gelatin, polyacrylamides, polyacrylic acids, polystyrene sulfonates, polyvinyl phosphonates, sodium carboxymethyl
30 cellulose and polysaccharides such as xanthan gum, alginates, and carageenin. The polymer content is from about 0.01% to about 20%, preferably from 0.05 to 10%, based on the weight of the mica pigment.

- 10 -

Any polyvalent cation which will form a precipitate with the polymer under given pH conditions can be used. Such polyvalent cations are employed in the form of a solution of a soluble salt. Thus, the cation can be, for example, one or more of Al(III), Cr(III), Zn(II), Mg(II), Ti(IV), Zr(IV), Fe(II), Fe(III), and Sn(IV). Suitable anions include chloride, nitrate, sulfate, and the like. The quantity of polyvalent metal ion is from about 0.01% to about 20%, preferably about 0.05% to about 10%, of the weight of the mica pigment.

The preferred pH range for deposition depends on the particular cation being employed. For Al and Cr(III), it is about 4.0 to 8.0. For Zr(IV), it is about 1.0 to 4.0. The metal salt solution is usually acidic, and the pH of the suspension is maintained at the desired range by addition of a soluble base, such as sodium hydroxide, potassium hydroxide, or ammonia solution. Where the desired pH of precipitation is lower than that of the salt solution, a soluble acid, such as HCl, is added as required.

The effect in each case is to deposit on the pigment platelets a complex of metal hydroxide or hydrous oxide and polymer which carries the particles of the absorption pigment with it, to produce a combination pigment with a smooth, adherent colored film on the platelets. After the deposition, the film can be fixed by washing and drying the combination pigment.

Colors may be adjusted if desired by mixing combination pigments. In general, it is preferred to mix pigments of the same or similar reflection color, since reflection colors mix additively and color intensity is reduced when very different reflection colors are mixed.

- 11 -

The absorption pigment components mix subtractively, and the usual pigment blending procedures are followed.

In order to further illustrate the invention, various non-limiting examples are set forth below. In these, as well as throughout the balance of this specification and claims, all parts and percentages are by weight and all temperatures are in degrees centigrade unless otherwise indicated.

Examples 1 - 4

10 A coating procedure was adopted in which 100 grams of C glass flakes (RCF-140 from Nippon Sheet Glass) having an average particle size of about 140 microns (by laser light scattering) were dispersed in 750 ml of water. Iron and zinc were introduced in the form of 1 ml of a 39% aqueous solution of ferric chloride and 7 ml of a 9% aqueous zinc chloride solution. The pH of the slurry was adjusted to 3.0 using a 35% aqueous sodium hydroxide solution and the slurry heated to a temperature of 76°C. The pH was then lowered to 1.6 by addition of hydrochloric acid and a 40% aqueous solution of titanium tetrachloride was added at a rate of 100 ml/hour while the pH was maintained at 1.6 by the addition of 35% aqueous sodium hydroxide. The titanium introduction was continued until an appearance of either a white pearl or the interference colors gold, red and blue had been reached. When the desired end point was achieved, the slurry was filtered on a Buchner funnel and washed with additional water. The coated platelets were then dried and calcined at 600°C.

30 Microscopy evaluation of the resulting pigment confirmed that the platelets are coated with a smooth homogeneous film layer of TiO_2 .

- 12 -

In addition, the luster and color of the resulting pigments were evaluated visually and instrumentally using drawdowns on a hiding chart (Form 2-6 Opacity Charts of The Leneta Company), half of which is black and half of which is white. A coating on the black part of this chart displays the reflection color and luster when it is examined specularly, while the coating on the white portion displays the transmission color when it is viewed at non specular angles. The drawdowns were prepared by incorporating 12% pigment in a nitrocellulose lacquer and applying this suspension to the black and white chart with a Bird film applicator bar.

When these cards were examined visually, pearlescent pigments with good luster and color intensity were observed. The appearance characteristics of these pigments were further characterized by determining the wavelength at which the reflectivity is a maximum and a minimum and the color described in terms of $L^*a^*b^*$. The $L^*a^*b^*$ data characterizes the appearance of a product in terms of its lightness-darkness component symbolized by L^* , a red-green component represented by a^* and a yellow-blue component symbolized by b^* . These measurements were made by using a goniospectrophotometer (GK-111 from Datacolor, Inc.).

Besides the appearance measurements, three of the pigments were also analyzed for the percentage of rutile and anatase that was present in each sample by x-ray diffraction. These results are all summarized in Table 2.

- 13 -

TABLE 2

Example	COLOR	λ_{max}	λ_{min}	Crystal Form	GK-111 12% Black 45/0		
					L*	a*	b*
2	Gold	570	700	Rutile	88.64	6.73	1.68
3	Red	630	540	Rutile	89.25	17.52	-5.78
4	Blue	670	570	Rutile	85.03	-3.32	-3.95

In all cases, a high-quality, high-luster rutile titanium dioxide-coated glass flake pearlescent pigment was obtained.

Example 5-11

One hundred grams of C glass flakes having an average particle size of 140 μm (RCF-140 from Nippon Sheet Glass) were dispersed in 333 ml of distilled water. This dispersion was heated to 74°C, and the pH adjusted to 1.6 using dilute hydrochloric acid. Then 7 ml of an 18% stannous chloride solution were slowly added. After the addition of the tin, a 40% aqueous solution of titanium tetrachloride was added at a rate of 100 ml/hr. The pH was maintained at 1.6 during the addition of the tin and titania by simultaneously adding a dilute aqueous solution of sodium hydroxide. The titania addition was continued until either a white pearl, interference colored gold, red, blue or green were observed. When the desired end point was reached, the slurry was filtered, washed with additional water and calcined at 600°C.

The resulting products were examined microscopically to verify that the TiO_2 was attached to the glass flakes in the form of a smooth homogeneous film layer. When drawn down, a series of vibrant, high quality colors were observed.

- 14 -

The color data and X-ray diffraction results for these products are summarized in Table 3. A high quality, high luster, rutile titanium dioxide coated glass flake pearlescent pigment was obtained in each case.

TABLE 3

Example	Color	$\lambda_{\text{max.}}$ (nm)	$\lambda_{\text{min.}}$ (nm)	Crystal Form	GK-111 Results		
					L*	a*	b*
5	Pearl	400	700	Rutile	73.55	-1.28	-2.59
6	Gold	630	700	Rutile	61.17	0.69	13.05
7	Orange	670	470	Rutile	59.75	8.00	10.27
8	Red	700	490	Rutile	60.47	8.95	2.85
9	Violet	400	520	Rutile	61.37	12.04	-8.86
10	Blue	440	580	Rutile	60.09	0.96	-9.95
11	Green	500	670	Rutile	60.06	-9.44	0.41

Examples 12 - 20

75 grams of C-glass flakes having an average size of 100 μm were dispersed in 300 ml of distilled water. The dispersion was heated to 76°C and the pH adjusted to 3.2 with dilute hydrochloric acid. A ferric chloride solution was added to the suspension at 0.2 ml/min while maintaining the pH at 3.2 using dilute sodium hydroxide. The ferric chloride addition was continued until the desired color was observed. At the appropriate end point, the slurry was filtered, washed with water and calcined at 600°C to yield an Fe_2O_3 coated glass flakes.

- 15 -

The resulting products were examined microscopically verifying that the Fe_2O_3 is attached to the glass flakes as a smooth, homogeneous film coating.

Since Fe_2O_3 has an inherent red color, glass flakes coated with this oxide have both a reflection color and an absorption color. The interference color is from the interference of light, while the absorption color is due to the absorption of light. The reflection color will change from gold to red to blue to green as increasing amounts of iron (III) oxide are coated on the glass flakes. As more iron (III) oxide is added, even thicker coatings of Fe_2O_3 are obtained which yield another series of interference colors known as the second order observable interference colors. These second order colors have even higher color intensity than the first colors along with higher coverage. If the coating process is continued even further, a third series of interference colors can be obtained.

When these iron oxide coated glass flakes were drawn down, a series of vivid, high quality colors were observed. Color data from these drawdowns was obtained and is summarized in Table 4.

- 16 -

TABLE 4

Example	MI 39% FeCl ₃	Interference Color	λ_{max} . (nm)	λ_{min} . (nm)	L*	a*	b*
12	48	1st Orange	665	400	75.64	13.50	21.63
13	66	1st Red	700	540	64.49	10.72	2.36
14	78	1st Violet-Blue	700	600	66.03	-2.66	0.35
15	90	1st Green	570	660	70.69	-5.34	8.28
16	102	2nd Orange	583	400	72.02	1.33	14.30
17	126	2nd Red	620	400	61.06	7.86	6.14
18	138	2nd Violet-Blue	590	400	56.17	3.48	2.35
19	150	2nd Green	700	400	54.24	-0.31	2.08
20	174	3rd Orange	590	400	51.46	1.48	2.67

Examples 21 - 23

The TiO₂ coatings also produce a series of interference colors as the thickness of the TiO₂ layer on the glass increases. Thin TiO₂ coatings produce a whitish reflection which appears pearly or silver. As the TiO₂ coating layer becomes thicker, gold, red, blue and green interference colors are observed. As the coating becomes even thicker, a series of second observable color is observed. These second colors have more color intensity and hiding than the first colors described in the Examples above.

These second colors were prepared by dispersing 50 gm of the glass flakes used in Examples 1-11 in 333 ml of distilled water. The pH was adjusted to 1.6 with dilute HCl, and the suspension was heated to 74°C. 7 ml of 18% stannous chloride were added followed by the addition of 40% titanium chloride at a rate of 0.33 ml/min. The pH was maintained at 1.6 by simultaneously adding dilute sodium hydroxide. The titania addition was continued until the desired second observable color was

- 17 -

observed. The slurry was filtered, washed with water and the resulting presscake calcined at 600°C to yield a TiO₂ coated glass flakes.

5 When drawn down, the resulting products have higher color intensity and more coverage than their comparable first observable interference colors. Color data from these drawdowns is summarized in Table 5.

TABLE 5

Example	Second Observable Interference Color	λ_{max} . (nm)	λ_{min} . (nm)	TiO ₂ Crystal Form	GK-111 Data		
					L*	a*	b*
10 21	Gold	580	430	Rutile	67.89	-3.54	10.88
22	Orange	640	480	Rutile	65.14	6.13	8.98
23	Red	680	510	Rutile	63.26	7.96	1.02

Examples 24 - 28

15 For comparative purposes, several examples of the aforementioned U.S. Patent 3,331,699 were repeated.

In the first instance, examples 1 and 2 of the patent in which glass was treated first with tin and then with titanyl sulfate were reproduced using E glass (REF-140 from Nippon Sheet Glass). The resulting products
 20 were examined using an optical microscope. The coatings were not smooth, and very little of the TiO₂ was actually attached to the surface of the glass flakes. When drawn down on the black and white cards, the resulting products had low luster, and exhibited no real interference
 25 effect. The patent's example 1 states that if a small portion of a dried sample was re-slurried in water, it would exhibit a lustrous sparkle. Accordingly, small quantities of the samples were redispersed in distilled

- 18 -

water. The reproduced sample from example 1 exhibited nothing except a milky suspension while the sample from Example 2 displayed a pale purple colored flake. The reproduced product of example 1 was calcined and a
5 mixture of anatase and rutile titanium dioxide was observed, but the product quality was poor.

Example 6 of the 3,331,699 Patent was also reproduced twice and resulted in a sequence of interference color pigments. In one reproduction, the
10 glass flake was a C glass (RCF-140 of Nippon Sheet Glass) and in the other reproduction it was E glass (REF-140 of Nippon Sheet Glass). When the pigments produced in these two examples were examined microscopically, some of the flakes were uncoated, and for those flakes that were
15 coated, the coatings were rough, contained many cracks and in some cases the coatings were peeling away from the surface of the glass. The pigments produced on the C glass were superior to their counterparts produced on the E glass. The C glass products were approximately 30%
20 rutile and 70% anatase while the E glass products were almost exclusively anatase.

Example 12 of the 3,331,699 patent, in which glass flakes were treated with tin and then with iron, was repeated using E glass (REF-140 of Nippon Sheet
25 Glass). The resulting product was a rust colored powder that exhibited primarily an absorption color effect. When a drawdown was prepared, the product exhibited very low luster and reflectivity. The products prepared in Examples 12-20 above were vastly superior.

30 Examples 29 - 30

The procedure of Example 5-11 was repeated except that an E glass was substituted for the C glass.

- 19 -

The TiO_2 coating was made which had a white, pearly appearance. The resulting E glass product had a titanium dioxide coating which was primarily anatase while the C glass products had 100% rutile titanium dioxide coatings and were much higher product quality. The color data is presented in Table 6.

TABLE 6

Example	Interference Color	λ_{max} (nm)	λ_{min} (nm)	Crystal Form	GK-111 12% Black 45/0		
					L*	a*	b*
29 (C-Glass)	Pearl	400	700	Rutile	73.64	-0.94	-2.36
30 (E-Glass)	Pearl	400	700	Anatase	73.44	-0.55	0.21

Example 31

An aqueous presscake of quinacridone red (Sunfast Red 19, Sun Chemical Co., 23.7% pigment) is diluted to 0.50% pigment with water. To 250 g of this suspension is added 0.1 g xanthan gum (Kelzan, a microbiolal polysaccharide containing a glucuronic acid, Kelco Division). Ultrasonic energy is applied by means of a Sonifier® Model 350 (Branson Sonic Power Co.) for 30 minutes to disperse the pigment.

The pearlescent glass substrate is 50 g of blue-reflecting pigment of Example 4, suspended by stirring in 400 g of water. The pH value of the suspension is 9.0, and is adjusted to 6.0 with 0.1 N HCl. This suspension was combined with the quinacridone red dispersion. A solution of 2.64 g $\text{CrCl}_3 \cdot 6\text{H}_2\text{O}$ in 165 g water is added at a uniform rate while maintaining the pH at 6.0 with 3.5% (by weight) NaOH. A smooth, uniform red coating is achieved. The suspension is filtered, and the

- 20 -

filter cake is washed with water. The filter cake was dried at 120°C for 1 hour.

Incorporated at 3% by weight in a paint vehicle of the following composition:

5	Acrylic resin thermosetting	51.78 Parts
	50% NV	
	Melamine, 60% NV	16.83 Parts
	Solvent, xylene	30.29 Parts

the combination pigment yields a two-color paint which, coated on a surface, has a blue highlight on a red background.

Example 32

A charge of 50 grams of the blue reflecting pigment of Example 4 in 800 ml of water were stirred at 60°C and the pH adjusted to 2 with a hydrochloric acid solution. A charge of about 64.7 grams of Sunfast blue colorant (7.5 g solids) were added and stirred for 30 minutes while adjusting the pH to 6 with 3.5% NaOH. Then a 2.4 aqueous solution of aluminum chloride hexahydrate was added at a rate of 1.5 ml/min and the pH maintained at 6 with the NaOH solution. The pH was raised to 7 and stirring continued for an additional 15 minutes. The product was recovered by filtering and the wet cake washed five times with 500 ml of water. It was then dried overnight at 90°C.

Examples 33-36

Example 32 was repeated four times employing Sunfast green colorant on a green colored rutile titanium dioxide coated glass (Example 33), Sunfast green colorant and the blue reflective pigment of Example 4 (Example 34), carbon black and a copper colored coated glass

- 21 -

pigment (Example 35) and carbon black in a violet colored pearlescent glass (Example 36). All of the resulting products were very attractive.

Various changes and modifications could be made in the process and products of this invention without departing from the spirit and scope thereof. The various embodiments which have been disclosed herein were for the purpose of further illustrating the invention but were not intended to limit it.

- 22 -

WHAT IS CLAIMED IS:

1. A pearlescent pigment comprising flakes of C glass having a first coating comprising iron oxide or rutile titanium dioxide thereon.

2. The pearlescent pigment of claim 1, in which the first coating comprises rutile titanium dioxide.

3. The pearlescent pigment of claim 1, in which the first coating comprises iron oxide.

4. The pearlescent pigment of claim 1, coated with a second layer comprising hydrous oxide or hydroxide of a polyvalent cation, precipitate of said polyvalent cation and an anionic polymeric substance, and water-insoluble colored pigment, the percentages of said cation, substance and pigment based on the weight of said pearlescent pigment being 0.01-20, 0.01-20, and 0.01-30, respectively.

5. The pearlescent pigment of claim 4, in which the first coating comprises rutile titanium dioxide.

6. The pearlescent pigment of claim 4, in which the first coating comprises iron oxide.

7. A method of forming a pearlescent pigment which comprises forming a first layer of hydrous rutile forming titanium dioxide or hydrous iron oxide on C glass flakes and calcining said layered flakes.

- 23 -

8. A method according to claim 7, in which a first layer of hydrous rutile forming titanium dioxide is deposited.

9. A method according to claim 8, in which the layer is formed by precipitating hydrous tin oxide on the surface of the glass flakes followed by depositing a layer of hydrous titanium dioxide thereon.

10. A method according to claim 7, in which the hydrous titanium dioxide is deposited on the glass flakes in the presence of iron and at least one member selected from the group consisting of calcium, magnesium and zinc ions.

11. A method according to claim 7, in which a first layer of hydrous iron oxide is deposited.

12. A method according to claim 7, wherein an aqueous suspension of the calcined flakes are combined with an aqueous suspension of water-insoluble colored pigment containing an anionic polymeric substance, combining the resulting suspension with an aqueous acidic solution of a polyvalent cation which forms a hydrous oxide or hydroxide precipitate and a precipitate with said substance at a given pH and a quantity of a pH adjustment agent to provide said given pH, and recovering the resulting colored pigment.

13. A method according to claim 12, in which a first layer of hydrous rutile forming titanium dioxide is deposited.

- 24 -

14. A method according to claim 12, in which a first layer is formed by precipitating hydrous tin oxide is precipitated on the surface of the glass flakes followed by depositing a layer of hydrous titanium dioxide thereon.

INTERNATIONAL SEARCH REPORT

Intern. Application No
PCT/US 97/09380A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C09C1/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C09C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	DATABASE WPI Week 9242 Derwent Publications Ltd., London, GB; AN 92-345112 XP002039404 & JP 04 249 584 A (TAYCA CORP.) , 4 September 1992 see abstract ---	1,7
A	DATABASE WPI Week 9421 Derwent Publications Ltd., London, GB; AN 94-173949 XP002039405 & JP 06 116 508 A (NIPPON SHEET GLASS CO.) , 26 April 1994 see abstract --- -/--	1,7

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

1 September 1997

Date of mailing of the international search report

12 09 97

Name and mailing address of the ISA
European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+ 31-70) 340-3016

Authorized officer

Van Bellingen, I

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 97/09380

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 3 331 699 A (W. J. MARSHALL ET AL.) 18 July 1967 cited in the application see claim 1 ---	1,7
A	EP 0 307 747 A (MERCK PATENT) 22 March 1989 see column 3, paragraph 4; claims 1,6 ---	1,7,9
A	DATABASE WPI Week 9421 Derwent Publications Ltd., London, GB; AN 94-173948 XP002039406 & JP 06 116 507 A (NIPPON SHEET GLASS CO.) , 26 April 1994 see abstract ---	1,7
A	DATABASE WPI Week 9421 Derwent Publications Ltd., London, GB; AN 94-173951 XP002039407 & JP 06 116 510 A (NIPPON SHEET GLASS CO.) , 26 April 1994 see abstract ---	1,7
A	DATABASE WPI Week 8818 Derwent Publications Ltd., London, GB; AN 88-123737 XP002039408 & JP 63 068 679 A (NIPPON PAINT CO.) , 28 March 1988 see abstract -----	

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No
PCT/US 97/09380

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 3331699 A	18-07-67	NONE	
EP 307747 A	22-03-89	DE 3730505 A	30-03-89
		CN 1031850 A,B	22-03-89
		CS 8806050 A	14-11-90
		DE 3871046 A	17-06-92
		FI 92599 B	31-08-94
		IN 169774 A	21-12-91
		JP 1101377 A	19-04-89
		KR 9609059 B	10-07-96
		US 5009711 A	23-04-91